



1647
E-glass Fabric

Product Data

STYLE	1647	Material: E-Glass	US System	SI Units
--------------	-------------	--------------------------	------------------	-----------------

Type of Yarns		Warp Yarn:	ECG 150 1/0	EC9 33
		Fill Yarn:	ECE 110 1/0	EC7 44
Fabric Weight, Dry			3.55 oz/yd ²	120 g/m ²
Weave Style		Plain		

CONSTRUCTION

Nominal Construction		Warp Count:	51/in	20.1/cm
		Fill Count:	30/in	11.8/cm
Fabric Thickness			4.1 mils	0.10 mm
Yarn Breaking Strength		Warp	180 lbf/in	158 daN/5cm
		Filling	180lbf/in	158 daN/5cm

Specifications	IPC 4412
-----------------------	----------

Availability	Limited
---------------------	---------

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered