



328
Para-Aramid Fabric

Product Data

| STYLE | 328 | Material: Kevlar 49 | US System | SI Units |
|-------------------------------|------------|----------------------------|-------------------------|----------------------|
| Type of Yarns | | Warp Yarn: | K49 1420d | K49 1420d |
| | | Fill Yarn: | K49 1420d | K49 1420d |
| Fabric Weight, Dry | | | 6.50 oz/yd ² | 220 g/m ² |
| Weave Style | | Plain | | |
| CONSTRUCTION | | | | |
| Nominal Construction | | Warp Count: | 17/in | 6.7/cm |
| | | Fill Count: | 17/in | 6.7/cm |
| Fabric Thickness | | | 12.8 mils | 0.33 mm |
| Yarn Breaking Strength | | Warp | 900 lbf/in | 788 daN/5cm |
| | | Filling | 900lbf/in | 788 daN/5cm |
| Specifications | | AMS 3902 Style 328 | | |
| Availability | | Very Limited | | |

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered