



348
Para-Aramid Fabric

Product Data

STYLE	348	Material: Kevlar 49	US System	SI Units
--------------	------------	----------------------------	------------------	-----------------

Type of Yarns		Warp Yarn:	K49 380d	K49 380d
----------------------	--	-------------------	----------	----------

		Fill Yarn:	K49 380d	K49 380d
--	--	-------------------	----------	----------

Fabric Weight, Dry			5.10 oz/yd ²	173 g/m ²
---------------------------	--	--	-------------------------	----------------------

Weave Style		8H Satin		
--------------------	--	----------	--	--

CONSTRUCTION

Nominal Construction		Warp Count:	50/in	19.7/cm
-----------------------------	--	--------------------	-------	---------

		Fill Count:	50/in	19.7/cm
--	--	--------------------	-------	---------

Fabric Thickness			8.7 mils	0.22 mm
-------------------------	--	--	----------	---------

Yarn Breaking Strength		Warp	650 lbf/in	569 daN/5cm
-------------------------------	--	-------------	------------	-------------

		Filling	650lbf/in	569 daN/5cm
--	--	----------------	-----------	-------------

Specifications		AMS 3902 Style 181		
-----------------------	--	--------------------	--	--

Availability		Very Limited		
---------------------	--	--------------	--	--

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered