



350
Para-Aramid Fabric
Product Data

STYLE	350	Material: Kevlar 49	US System	SI Units
--------------	------------	----------------------------	------------------	-----------------

Type of Yarns		Warp Yarn:	K49 195d	K49 195d
----------------------	--	-------------------	----------	----------

		Fill Yarn:	K49 195d	K49 195d
--	--	-------------------	----------	----------

Fabric Weight, Dry			1.80 oz/yd ²	61 g/m ²
---------------------------	--	--	-------------------------	---------------------

Weave Style		Plain		
--------------------	--	-------	--	--

CONSTRUCTION

Nominal Construction		Warp Count:	34/in	13.4/cm
-----------------------------	--	--------------------	-------	---------

		Fill Count:	34/in	13.4/cm
--	--	--------------------	-------	---------

Fabric Thickness			3.9 mils	0.10 mm
-------------------------	--	--	----------	---------

Yarn Breaking Strength		Warp	200 lbf/in	175 daN/5cm
-------------------------------	--	-------------	------------	-------------

		Filling	200lbf/in	175 daN/5cm
--	--	----------------	-----------	-------------

Specifications		AMS 3902 Style 120		
-----------------------	--	--------------------	--	--

Availability		Common		
---------------------	--	--------	--	--

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered