

## 4039

## **Para-Aramid Fabric**

## **Product Data**

STYLE 4039 Mate	rial: Kevlar KM2+	US System	SI Units
Type of Yarns	Warp Yarn:	KM2+ 600d	KM2+ 600d
	Fill Yarn:	KM2+ 600d	KM2+ 600d
Fabric Weight, Dry		4.50 oz/yd <sup>2</sup>	153 g/m <sup>2</sup>
Weave Style	Plain		
CONSTRUCTION			
Nominal Construction	Warp Count:	29/in	11.4/cm
	Fill Count:	29/in	11.4/cm
Fabric Thickness		8.4 mils	0.21 mm
Yarn Breaking Strength	Warp	700 lbf/in	613 daN/5cm
	Filling	700lbf/in	613 daN/5cm
Specifications			
Availability	Common		
IMPORTANT			

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

## FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials PO Box 2627 Anderson, SC 29622 USA

Phone: 800-431-1110 Fax: 864-260-6581 ISO 9001 Registered