



527
Astroquartz® Fabric
Product Data

STYLE 527 **Material: Astroquartz II** **US System** **SI Units**

Type of Yarns **Warp Yarn:** QCG 300 2/2 QC9 16.5 x2 x2
 Fill Yarn: QCG 300 2/2 QC9 16.5 x2 x2

Fabric Weight, Dry 6.10 oz/yd² 207 g/m²

Weave Style Plain

CONSTRUCTION

Nominal Construction **Warp Count:** 42/in 16.5/cm
 Fill Count: 32/in 12.6/cm

Fabric Thickness 8.0 mils 0.20 mm

Yarn Breaking Strength **Warp** 270 lbf/in 236 daN/5cm
 Filling 250lbf/in 219 daN/5cm

Specifications AMS 3846

Availability Limited

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered