5353

Para-Aramid Fabric

Product Data

STYLE 5353	**Material: Twaron 2200**	**US System**	**SI Units**
Type of Yarns	***Warp Yarn:***	T2200 1270dt	T2200 1270dt
	Fill Yarn:	T2200 1270dt	T2200 1270dt
Fabric Weight, Dry		5.20 oz/yd^2	176 g/m^2
Weave Style	4H Satin		

CONSTRUCTION

Nominal Construction	***Warp Count:***	17/in	6.7/cm
	Fill Count:	17/in	6.7/cm
Fabric Thickness		9.7 mils	0.25 mm
Yarn Breaking Strength	***Warp***	750 lbf/in	657 daN/5cm
	Filling	750lbf/in	657 daN/5cm
Specifications	AMS 3902 Style 285	BMS 8-381 Style 285	
Availability	Common		

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US

JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered