



5354
Para-Aramid Fabric

Product Data

STYLE	5354	Material: Twaron 2200	US System	SI Units
Type of Yarns		Warp Yarn:	T2200 1580dt	T2200 1580dt
		Fill Yarn:	T2200 1580dt	T2200 1580dt
Fabric Weight, Dry			4.90 oz/yd ²	166 g/m ²
Weave Style		Plain		
<hr/> CONSTRUCTION <hr/>				
Nominal Construction		Warp Count:	13/in	5. /cm
		Fill Count:	13/in	5. /cm
Fabric Thickness			10.0 mils	0.25 mm
Yarn Breaking Strength		Warp	550 lbf/in	482 daN/5cm
		Filling	550lbf/in	482 daN/5cm
<hr/>				
Specifications		AMS 3902 Style 500		
<hr/>				
Availability		Very Limited		

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
 PO Box 2627
 Anderson, SC 29622
 USA
 Phone: 800-431-1110
 Fax: 864-260-6581
 ISO 9001 Registered