



5383
Para-Aramid Fabric
Product Data

STYLE 5383 **Material: Twaron 2200** **US System** **SI Units**

Type of Yarns	Warp Yarn:	T2200 2420dt	T2200 2420dt
	Fill Yarn:	T2200 2420dt	T2200 2420dt
Fabric Weight, Dry		9.10 oz/yd ²	308 g/m ²
Weave Style	5H Satin		

CONSTRUCTION

Nominal Construction	Warp Count:	16/in	6.3/cm
	Fill Count:	16/in	6.3/cm
Fabric Thickness		13.0 mils	0.33 mm
Yarn Breaking Strength	Warp	920 lbf/in	806 daN/5cm
	Filling	970lbf/in	849 daN/5cm

Specifications AMS 3902 Style 900

Availability Very Limited

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered