



5384
Para-Aramid Fabric
Product Data

STYLE 5384 **Material: Twaron 2200** **US System** **SI Units**

| | | | |
|---------------------------|-------------------|--------------------------|----------------------|
| Type of Yarns | Warp Yarn: | T2200 1580dt | T2200 1580dt |
| | Fill Yarn: | T2200 1580dt | T2200 1580dt |
| Fabric Weight, Dry | | 10.70 oz/yd ² | 363 g/m ² |
| Weave Style | | Basket 4x4 | |

CONSTRUCTION

| | | | |
|-------------------------------|--------------------|-------------|--------------|
| Nominal Construction | Warp Count: | 28/in | 11/cm |
| | Fill Count: | 28/in | 11/cm |
| Fabric Thickness | | 19.0 mils | 0.48 mm |
| Yarn Breaking Strength | Warp | 1360 lbf/in | 1191 daN/5cm |
| | Filling | 1360lbf/in | 1191 daN/5cm |

Specifications AMS 3902 style 1050

Availability Very Limited

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered