



5388
Para-Aramid Fabric
Product Data

STYLE	5388	Material: Twaron 2200	US System	SI Units
--------------	------	------------------------------	------------------	-----------------

Type of Yarns	Warp Yarn:	T2200 1580dt	T2200 1580dt
	Fill Yarn:	T2200 1580dt	T2200 1580dt
Fabric Weight, Dry		15.50 oz/yd ²	525 g/m ²
Weave Style		Basket 8x8	

CONSTRUCTION

Nominal Construction	Warp Count:	40/in	15.7/cm
	Fill Count:	40/in	15.7/cm
Fabric Thickness		26.9 mils	0.68 mm
Yarn Breaking Strength	Warp	1830 lbf/in	1602 daN/5cm
	Filling	1790lbf/in	1567 daN/5cm

Specifications	AMS 3902 Style 1033
-----------------------	---------------------

Availability	Very Limited
---------------------	--------------

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered