



5768
Para-Aramid Fabric
Product Data

STYLE 5768 **Material: Twaron 2040** **US System** **SI Units**

| | | | |
|---------------------------|-------------------|-------------------------|----------------------|
| Type of Yarns | Warp Yarn: | T2040 550dt | T2040 550dt |
| | Fill Yarn: | T2040 550dt | T2040 550dt |
| Fabric Weight, Dry | | 3.60 oz/yd ² | 122 g/m ² |
| Weave Style | Plain | | |

CONSTRUCTION

| | | | |
|-------------------------------|--------------------|------------|-------------|
| Nominal Construction | Warp Count: | 28/in | 11/cm |
| | Fill Count: | 28/in | 11/cm |
| Fabric Thickness | | 6.5 mils | 0.17 mm |
| Yarn Breaking Strength | Warp | 500 lbf/in | 438 daN/5cm |
| | Filling | 500lbf/in | 438 daN/5cm |

Specifications

Availability Common

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered