



750
Para-Aramid Fabric
Product Data

STYLE	750	Material: Kevlar KM2+	US System	SI Units
--------------	-----	------------------------------	------------------	-----------------

Type of Yarns	Warp Yarn:	KM2+ 600d	KM2+ 600d
	Fill Yarn:	KM2+ 600d	KM2+ 600d
Fabric Weight, Dry		3.80 oz/yd ²	129 g/m ²
Weave Style	2x2 Twill		

CONSTRUCTION

Nominal Construction	Warp Count:	24/in	9.4/cm
	Fill Count:	24/in	9.4/cm
Fabric Thickness		6.9 mils	0.18 mm
Yarn Breaking Strength	Warp	720 lbf/in	630 daN/5cm
	Filling	680lbf/in	595 daN/5cm

Specifications

Availability	Limited
---------------------	---------

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered