



775
Para-Aramid Fabric
Product Data

STYLE	775	Material: Kevlar KM2+	US System	SI Units
--------------	------------	------------------------------	------------------	-----------------

Type of Yarns	Warp Yarn:	KM2+ 850d	KM2+ 850d
	Fill Yarn:	KM2+ 850d	KM2+ 850d
Fabric Weight, Dry		6.80 oz/yd ²	231 g/m ²
Weave Style	Plain		

CONSTRUCTION

Nominal Construction	Warp Count:	31/in	12.2/cm
	Fill Count:	31/in	12.2/cm
Fabric Thickness		11.8 mils	0.30 mm
Yarn Breaking Strength	Warp	880 lbf/in	771 daN/5cm
	Filling	950lbf/in	832 daN/5cm

Specifications

Availability	Common
---------------------	--------

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



JPS Composite Materials
PO Box 2627
Anderson, SC 29622
USA
Phone: 800-431-1110
Fax: 864-260-6581
ISO 9001 Registered